

บทคัดย่อภาษาไทย

สารประกอบคอมโพสิต $2\text{LiBH}_4\text{-MgH}_2\text{-TiCl}_3$ ในวัสดุพูนคาร์บอนระดับนาโนเมตรเพื่อใช้เป็นแหล่งเก็บกักไฮโดรเจนที่เกิดปฏิกิริยาผันกลับได้ถูกเสนอในโครงการวิจัยฉบับนี้ 1.6 wt. % TiCl_3 ถูกห่อหุ้มด้วย RF-CAS โดยวิธีการแช่ นอกจากนี้มันยังถูกบรรจุในระดับนาโนเมตรกับ $2\text{LiBH}_4\text{-MgH}_2$ โดยผ่านการหลอมให้ซึมเข้าไป ปฏิกิริยาการปลดปล่อยไฮโดรเจนเกิดได้เร็วขึ้นหลังจากที่มีการเติม TiCl_3 เข้าไป สำหรับสารประกอบคอมโพสิต $2\text{LiBH}_4\text{-MgH}_2\text{-TiCl}_3$ ในวัสดุพูนคาร์บอนระดับนาโนเมตร การปลดปล่อยปริมาณไฮโดรเจน 95 % ของปริมาณไฮโดรเจนทั้งหมดจะใช้เวลาประมาณ 1 และ 4.5 ชั่วโมง ในการเกิดปฏิกิริยาครั้งที่ 1 และ 2 ตามลำดับ ในขณะที่สารประกอบคอมโพสิต $2\text{LiBH}_4\text{-MgH}_2$ ในวัสดุพูนคาร์บอนระดับนาโนเมตรใช้เวลาตั้ง 2.5 และ 7 ชั่วโมง ตามลำดับ ส่วนวัสดุคอมโพสิต $2\text{LiBH}_4\text{-MgH}_2$ ใช้เวลาตั้ง 23 และ 22 ชั่วโมง ตามลำดับ ซึ่งเป็นการใช้เวลานานมาก นอกจากนี้การปลดปล่อยไฮโดรเจนของสารประกอบคอมโพสิต $2\text{LiBH}_4\text{-MgH}_2\text{-TiCl}_3$ ในวัสดุพูนคาร์บอนระดับนาโนเมตร หลังจากรอบที่ 4 แล้วยังได้ตั้ง 95-98.6% ของทฤษฎีความจุของไฮโดรเจน ซึ่งก็คือ 3.6-3.75 wt. % H_2 การเกิดปฏิกิริยาแบบผันกลับได้ของวัสดุนี้ถูกยืนยันจากการก่อตัวของ LiBH_4 และ MgH_2 หลังการเกิดปฏิกิริยาเก็บกักไฮโดรเจน (rehydrogenation) ซึ่งจะตรวจสอบได้โดย FTIR และ SR-PXD ตามลำดับ

บทคัดย่อภาษาอังกฤษ

Nanoconfinement of $2\text{LiBH}_4\text{-MgH}_2\text{-TiCl}_3$ in resorcinol-formaldehyde carbon aerogel scaffold (RF-CAS) for reversible hydrogen storage applications is proposed. RF-CAS is encapsulated with approximately 1.6 wt. % TiCl_3 by solution impregnation technique, and it is further nanoconfined with bulk $2\text{LiBH}_4\text{-MgH}_2$ via melt infiltration. Faster dehydrogenation kinetics is obtained after TiCl_3 impregnation, for example, nanoconfined $2\text{LiBH}_4\text{-MgH}_2\text{-TiCl}_3$ requires ~1 and 4.5 h, respectively, to release 95% of the total hydrogen content during the 1st and 2nd cycles, while nanoconfined $2\text{LiBH}_4\text{-MgH}_2$ (~2.5 and 7 h, respectively) and bulk material (~23 and 22 h, respectively) take considerably longer. Moreover, 95-98.6% of the theoretical H_2 storage capacity (3.6-3.75 wt. % H_2) is reproduced after four hydrogen release and uptake cycles of the nanoconfined $2\text{LiBH}_4\text{-MgH}_2\text{-TiCl}_3$. The reversibility of this hydrogen storage material is confirmed by the formation of LiBH_4 and MgH_2 after rehydrogenation using FTIR and SR-PXD techniques, respectively.

